



MULTIS EP 0

DESCRIPTION

Multi-purpose Extreme Pressure semi-fluid Lithium/Calcium grease.

APPLICATIONS

MULTIS EP 0 is especially developed for chassis lubrication by means of a centralized system for which NLGI 0 grade greases are recommended.

Central lubrication systems found on trucks, off-road vehicles used in agriculture civil engineering, and industry.

SPECIFICATIONS

ISO 6743-9: L - XCCEB 0

DIN 51502: MP0K -35

ADVANTAGES

Forms a durable lubrication film, resulting in prolonged lifetime of the lubricated parts.

MULTIS EP 0, because of its excellent low temperature characteristics and smooth texture has an outstanding pumpability.

MULTIS EP 0 is miscible with most other conventional soap greases.

Excellent adhesion to metal.

MULTIS EP 0 does not contain lead, or other heavy metals considered harmful to human health and the environment.

This lubricant used as recommended and for the application for which it has been designed does not present any particular risk.

A material safety data sheet conforming to the regulations in use in the E.C. is obtainable via your commercial adviser www.quick-fds.com.

TotalEnergies Lubricants

SA 552 006 454 RCS Nanterre - France

RECOMMENDATIONS

Always avoid contamination of the grease by dust and/or dirt when applying. Preferably use a pneumatic pump system.

TYPICAL CHARACTERISTICS

PROPERTIES	METHODS	UNITS	MULTIS EP 0
Soap/thickener		-	Lithium/ Calcium
NLGI Grade	ASTM D 217/DIN 51 818	-	0
Color	Visual	-	Brown
Appearance	Visual	-	Smooth
Operating temperature range		°C	-35 à 120
Penetration at 25°C	ASTM D 217/DIN 51 818	0.1 mm	355-385
Flow pressure 1400 mbar	DIN 51 805	°C	-35
Delimon 7mm, -20°C, 1/10/100 g/min	DIN 51 816-T2	Bar/m	1.7/6.5/30
Dropping point	IP 396/DIN ISO 2176	°C	>170
Kinematic viscosity of the base oil at 40°C	ASTM D 445/DIN 51 562-1/ISO 3104/IP71	mm ² /s (cSt)	150
4b weld load	ASTM D 2596	Kgf	315
4b wear scar	ASTM D 2266	mm	0,6

Above characteristics are mean values given as an information.

This lubricant used as recommended and for the application for which it has been designed does not present any particular risk.

A material safety data sheet conforming to the regulations in use in the E.C. is obtainable via your commercial adviser www.quick-fds.com.

TotalEnergies Lubricants

SA 552 006 454 RCS Nanterre - France